

## Oil for weapons 200 ml (OL106)

This is another Ambro-Sol amazing product. This oil is ideal for cleaning and protect all types of weapon. It prevents the penetration of humidity, dust and corrosive substances.



**HOW TO USE:** Shake well before use. Apply directly on the surface / workpiece using a cloth or brush to clean and remove carbon residues. Apply again the product on the surface / piece with a cloth or a brush for lasting protection.

## MODALITY OF STORAGE

Before using: stock the product in a dry location and don't stock it with a temperature under 0° degrees and over 45°C, after the use, keep containers closed. In the original package, the product can be conserved for 24 months.

After the first usage: conserve in a fresh and dry location, away from hot spring. Keep out of reach of children.

## Hazards identification:

H222	Extremely flammable aerosol.
H229	Pressurized container: it may burst if heated.
H336	May cause drowsiness or dizziness.

This information, even if reliable, must be considered only approximate. The usage don't imply our responsibility, included the violation of many license. Before using, the users have to verify the suitability of the product for the specific use



Ambro-Sol - 25020 Cigole (BS) Italy - <u>www.gnocchiecospray.com</u> - <u>www.ambro-sol.com</u> - <u>info@ambro-sol.com</u>

Quantity	200 ml
Barcode	EAN 13: 8034108890173
Confection:	12 pz

**WEAPONS OIL** – Protective, anti-corrosive lubricant for weapons. Extra fine oil with elevated penetration and cleaning properties. Fundamental for the maintenance of all types of weapons. It forms a protective barrier against humidity, water, and the corrosive substances in gun powder.

## **Technical Specifications:**

Aspect	Cylinder containing under pressure fluid
Color	Light brown
Odour	Characteristic of solvent
Relative density	a 20°C 0,67 ÷ 0,71 g/ml
Flash point	0° C
Pressure at 20°C	4/6 bar
Viscosity Oil at 40°C	>11 cSt
Viscosity Oil at 20°C	mm2/s 25 ASTM D 445
Thickness of the dry film	2.0 µ m(content oil)
Pour point	-35 °C (content oil)
Wearing test	(ASTM –D-2266) 0.5 mm(content oil)
Wet room	550 ore ASTM D 1748 (content oil)
Salt fog	9 ore ASTM B 117 (content oil)
Covering power	m2/I 80 L.F.(content oil)